

Technical Data

Truguard Smooth Masonry

A smooth, durable coating, which maintains and enhances the original texture of the underlying surface. Suitable for most exterior masonry surfaces, offering excellent resistance to the accumulation of dirt, protecting against weathering and atmospheric pollution. The anti-carbonation properties also resist the ingress of carbon dioxide from car exhaust fumes and prevent deterioration of concrete and steel



The British Board of Agrément is designated by Government to issue European Technical Approvals based on the assessment of products for construction. Leyland's products carrying this logo have undergone rigorous independent testing and received approval from the BBA.

Recommended uses

Interior X

Exterior

Type of substrate

Concrete, cement rendering, brick, stone, blockwork and pebbledash.

Colour availability

Brilliant White and a range of ready mixed colours (10ltr and 5ltr). Thousands of tinted colours also available (10ltr and 5ltr).

Finish

Matt

Volume solid

30%

Coverage

1 litre will cover approximately 10 square metres on smooth surfaces. In common with all wall paints, the spreading rate will be reduced on rough and absorbent surfaces such as pebbledash. When using more than one tin of a colour, it is advised that you intermix the quantity required beforehand.

Drying time

Touch dry in 1-2 hours. Recoatable after 4-6 hours.

Transportation and storage

To avoid the risk of spillage, always store and transport in a secure upright position.

Protect from frost.

VOC content

LOW VOC CONTENT 0.30-7.99% VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/c): 40g/l (2010). This product contains max 30g/l VOC.

Film thickness

Wet: 100µm Dry: 30µm

Preparation

Ensure surface to be painted is sound, clean, dry and free from grease. Treat any mould or lichen with Sterilisation Wash as directed. Truguard Smooth Masonry can be applied directly over bare and previously painted surfaces provided these are clean, sound and firm. Chalky, underbound surfaces should be scraped, dry brushed and then given a coat of Truguard Stabilising Masonry Primer. Remove any limewash or distemper completely. Wear a suitable face mask if creating dust. Before applying Truguard Stabilising Masonry Primer to the whole surface, first carry out a test application to a small area. If this dries to a glossy film, thin with one part of White Spirit to two parts of Truguard Stabilising Masonry Primer and then test again in another small area. It is important to ensure that a non-glossy, dried, sealed surface is produced.

Application

Stir well before use. Do not thin, except for absorbent surfaces, when a small quantity of clean water may be added. Apply two full coats, allowing 4-6 hours between coats under normal drying conditions. Do not apply when air or surface temperatures are below 10°C, or when rain is imminent. Suitable for application by brush, roller, conventional and airless spray.

Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Some local authorities have special facilities for disposal of waste coatings. Do not empty product into drains or watercourses. Replace lid firmly.

Warning

- Contains 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.
- Safety data sheet available on request.
- If medical advice is needed, have product container or label at hand.
- Keep out of reach of children.
- Dispose of contents/container to a waste disposal site in accordance with local/national regulations.
- Ensure good ventilation during application and dryina.
- Do not breathe spray. Wear respiratory protection.
- Do not get in eyes, on skin, or on clothing.
- IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- IF ON SKIN: Wash with plenty of water. Do not use solvent thinners or White Spirit.
- IF SWALLOWED: Call a POISON CENTRE or doctor if you feel unwell.