

SATIN FINISH

A solvent-borne highly durable, washable satin finish for interior joinery and metalwork. Does not always require an undercoat.

AVAILABILITY

Colour Range	Refer to current Crown Trade Literature.
Packaging	1, 2.5, and 5 litre.

PROPERTIES

Drying Time	Under normal drying conditions touch dry in 4-6 hours and recoatable after 16 hours. Allow for adequate ventilation during the drying period.
Finish	Satin.
Composition	Pigment: Titanium Dioxide, coloured pigments and extenders. Binder: Thixotropic alkyd. Alkyd Solvent: Dearomatised White Spirit.
Spreading Rate	Up to 16m ² per litre on smooth surfaces.
Wet Film Thickness	62.5 micrometres at 16m ² per litre
Dry Film Thickness	35 micrometres at 16m ² per litre.
Volume Solids	56% Brilliant White other colours will vary.
Flash Point	40°C (closed cup).
VOC Content	EU limit value for this product (cat.A/d): 300 g/l (2010). This product contains max. 299 g/l VOC.
Limitations	For interior use only. Do not apply when air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

PREPARATION

New Surfaces

Timber

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Rub down with a suitable grade of abrasive paper and round sharp edges 1-3mm. Remove all dust. Treat knots with two thin coats of fresh knotting. Fill any fixing holes, open joints and shallow surface defects with Sandtex Trade Ready Mixed Filler. Rub down with a suitable grade of abrasive paper. Remove all dust. Prime with one coat of Crown Trade Wood Primer as required. Prior to priming the moisture content should not exceed 18%.

All metals including galvanised

Surfaces must be clean and free from anything that will interfere with the materials to be applied. Wash with hot water and liquid detergent solution to remove oil, grease or any other contaminants, frequently changing the water. Rinse thoroughly with clean water. Allow to dry. Galvanised surfaces should be pre-treated with Crown Trade Protective Coatings T-Wash. Overall blackening of the surface will confirm satisfactory surface preparation.

Non-ferrous metals

Lightly abrade to a bright (not polished) surface - excluding galvanised surfaces. Rinse thoroughly with clean water to remove all residues. Allow to dry. Prime, including galvanised surfaces, with one coat of Crown Trade Universal Metal Primer.

Additional surface preparation – all metals

Ferrous metals

Remove all millscale and rust back to clean metal. Remove all residues. Prime within the working day with one coat of Crown Trade Universal Metal Primer.

Previously decorated surfaces

Timber

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect paint. Prior to painting the moisture should not exceed 18%. Remove grey and denatured surfaces by rubbing down with abrasive paper or by mechanical means. Feather edges of sound paint. Remove all dust. Organic growth must be removed and the areas treated with Crown Trade Fungicidal Solution. Treat knots with two thin coats of fresh knotting solution. Fill any fixing holes, open joints and shallow surface defects with Sandtex Trade Ready Mixed Filler or a two pack proprietary wood filler. Rub down with a suitable grade of abrasive paper. Remove all dust.

Metals

All surfaces must be suitably dry, and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose and failing or suspect paint. Feather edges of sound paint. Remove all dust. Remove all rust. Spot prime ferrous metals with one coat of Crown Trade Universal Metal Primer. Spot prime nonferrous metals including galvanised metal with one coat of Crown Trade Universal Metal Primer.

Timber and metals

Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. Bring forward spot primed area with one coat of Crown Trade Satin Finish.

COATING SYSTEM

Apply one or two coats Satin Finish to new or previously painted surfaces as required. Maintain a wet edge.

APPLICATION

Stir well before use. Apply by brush to an even thickness (a fine, soft long filament bristle brush gives best results). Maintain a wet edge. On timber lay off in the direction of the grain. Always intermix packs for colour consistency. Please check for colour accuracy prior to application. Crown Paints is not liable for decorating costs caused as a result of an incorrect colour being applied. NOTE: Our products are formulated to the highest quality, however recent changes made to meet the reduced solvent levels required by current legislation may in certain circumstances, such as lack of daylight, lead to white and very pale colours yellowing over time.

MAINTANANCE FOR CDM FILE

Prior to priming the moisture content should not exceed 18%.

CLEANING

Return surplus material to container. Clean with a proprietary cleaner immediately after use.

HEALTH AND SAFETY

Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Crown Trade Customer Relations Team. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Crown Paints products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Crown Paints is unable to guarantee results as it has no control over the conditions under which its products are applied.

Before using this product please ensure you have the latest information. For help or more information contact the Crown Trade Customer Relations Team on:

Tel: 0845 389 9583

Fax: 0845 389 9584

e-mail: info@crowntrade.co.uk

website: www.crowntrade.co.uk

This information is correct at date of issue October 2011.



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG

Tel: 01254 704951 Fax: 01254 870155

Email: info@crowntrade.co.uk

Website: www.crowntrade.co.uk